

**SYNTHESIZES AND PERFORMANCE OF POLY (ETHYLENE  
GLYCOL TERPHTHALATE DIMETHYL SILOXANE)  
COMPOUND AS PROTECTIVE MATERIAL FOR CARBON  
STEEL ALLOY OF PETROLEUM PIPELINES**

**Abo-Elenien, O. M. and Abu-Alainin, H. M\*.**

Egyptian Petroleum Research Institute (EPRI), Ahmed El-Zomor St., #1,  
Nasr City 11727, Cairo, Egypt.

\*Faculty of Engineering, Production and Design Department(61111).  
Elminia Univ., Elminia, Egypt.

**ABSTRACT**

The poly (ethylene glycol terphthalate dimethylsiloxane) compound [PEGTDMSO] was prepared and confirmed by FT. IR, NMR and GPC techniques. The carbon steel alloy specimens were provided from unused petroleum pipelines. PEGTDMSO was formulated with  $TiO_2$ ,  $ZnO_2$ , and different ratios of silica gel as inorganic additives to produce seven formula designated from  $Y_0$ -  $Y_6$ . The toluene diisocyanate (TDI) was used as curing agent. The visual inspection, physical, mechanical and chemical properties such as, wet film thickness (WFT), dry film thickness (DFT), adhesion forces, bending, impact, hardness and thermal stability at 150 - 400 °C at intervals of 50 °C. Acid effect (10%  $H_2SO_4$ ) at period time of 480 hr and the sealant water effect at period time of 1440 hr for the formed dry films were studied. The results indicated that the corrosion spots did not detect on the surface of the formed dry films from formula  $Y_2$ - $Y_6$ . These films approved to be a protecting agent for the surface of petroleum pipelines against corrosion.

**INTRODUCTION**

The carbon steel alloys are used at high temperatures in large scale for production and manufacture of petroleum, petrochemical equipments and different industries. The carbon steel alloys are corroded

quickly when subjected to both chemical and physical environmental conditions [ Delamo, et. al. (1998) Sidky, and Hocking (1999); Alagar, et. al. (1999); Abo-Elenien, et. al. (2000, 2004); Uyanik, et. al. (2001); Claudia, et. al. (2002) and Abd El Rahman (2004)].

The types of protective coatings must be compatible with the metal surfaces without any change. The formed films act as a barrier between the metallic surfaces and the surrounding corrosive medium. These include paints, varnishes, enamels, plastics and metals which were applied by brushing, electroplating, hot dipping flame spraying, etc. [Sayal (1981); Delamo, et. al. (1998); Mayer (1998); Townsend (1998) Tiwari and Saxena (1999); Alagar, et. al. (1999); Zeh (2000); Fream and Magent (2000); Cackovich and Perry (2000); Abo-Elenien, et. al. (2000, 2004); Macqueen and Blum (2001); Uyanik, et. al. (2001); Claudia, et. al. (2002) and Kim, et. al. (2002)].

Paintings are one of the most suitable, less expensive, and more efficient methods for corrosion and wear control, which could be more suitable binders source and high efficiency as protective compounds. [Sayal (1981); Sue and Troue (1987); Delamo, et. al. (1998); Mayer (1998); Townsend (1998); Tiwari and Saxena (1999); Alagar, et. al. (1999); Sidky and Hocking (1999); Zeh (2000); Fream and Magent (2000); Cackovich and Perry (2000); Abo-Elenien and Abu-Alainin (2000); Macqueen and Blum (2001) Uyanik, et. al. (2001); Claudia, et. al. (2002) and Kim, et. al. (2002)].


The aim of this work is to synthesize PEGTDMSO and formulate it with inorganic ZnO, TiO<sub>2</sub>, and silica gel. The different ratio of curing agent TDI is used. The prepared surface of carbon steel alloy specimens AG-15 are coated by these formulae.

## EXPERIMENTAL METHODS

### Preparation of PEGTDMSO

The Preparation of PEGTDMSO was carried out by reacting of 1.0 mol of terephthalic acid with 1.0 mol of ethylene glycol in a three-necked flask under mechanical stirring. After cooling the reaction mixture, dichlorodimethylsilane was added dropwise in an inert media. The product PEGTDMSO was purified and confirmed by Infrared analysis (FTIR), Nuclear magnetic resonance <sup>1</sup>H NMR and molecular weight determination (M.Wt) by gel permeation chromatography (GPC).

The PEGTDMSO was prepared through the reaction of ethylene glycol, terephthalic acid and dimethyl-dichlorosilane in presence of pyridine as acid acceptor according to the following equation:-



Where, n = M. Wt of poly(ethylene terephthalate) and m = M. Wt of PEGTDMSO

#### Preparation of the painting formula

45 parts of PEGTDMSO compound were mixed with 35 parts of zinc oxide, 5 parts of  $\text{TiO}_2$  and different ratios of silica gel. The 5 parts of organic solvent mixture of (xylene, toluene and methylethylketone (MEK)) were used. The toluene-di-isocyanate (TDI) was used at three concentrated ratios(5, 10 & 15 %) as a curing agent, which were mixed with each other to form various formulation designated from  $Y_0$ - $Y_6$ . These formulations were applied on the prepared surface of carbon steel alloy specimens by brushing method.

#### Preparation of the surface metal specimens

Unused tubes of carbon steel alloy type AG-15 were provided from petroleum pipelines of Belayim Petroleum Company at Port -Fouad station to be used as specimens supplier. The specimens were cut as regular edged cuboids with dimensions  $\approx 8, 15, 0.1$  cm average. Each specimen was cleaned, polished with 150, 400, 600 emery paper, rinsed with distilled water, degreased with acetone, weight and finally stored



under vacuum after wrapping with adhesive thin paper into sets. Each set includes specimens having nearly similar weight and surface area.

#### **The optimization steps**

To obtain the optimum PEGTDMSO coatings were carried out under static air, at ambient pressure and temperature within a selection formula from  $Y_0$  to  $Y_6$ . A set of specimens were coated with these formula and cured by curing agent TDI at ambient condition. The coating specimens were gradually inspected to recorded the optimization conditions for each formula. The coating films over the surface of specimens were examined by measuring the WFT, DFT, adhesion, thermal stability, impact, bending, hardness and chemical tests.

The formation of the best coating was achieved in steps and kept constant through the optimization procedure.

#### **The characterization techniques**

##### **Visual inspection**

The visual inspection for the formation coating as sealing, sagging, fish eyes, shirinking, cogulation, smoothes and homogeneity were inspected and tabulated.

##### **Physical properties**

Wet film thickness(WFT), dry film thickness(DFT), adhesion, thermal cycling test, Electrical conductivity, and Pinhole test of the formed coatings were carried out according to ASTM (D-1212), (D-1186 and 1005), (D 3359), BS-6670 Part 5 BS-6670 Part 5, ASTM (D-4399) and (D-5162), respectively.

##### **Mechanical properties**

Bending, adhesion forces, hardness, and impact tests were carried out according to ASTM (D-522), (D- 3363) and ASTM (D-2794 and G14-88), respectively.

##### **Chemical properties**

The effect of organic solvents, 10%  $H_2SO_4$  and synthetic sea water 3.5% NaCl were carried out according to ASTM D-44, 4752, 468, 610, G-31 and BS-6670, respectively. The data of results were recorded and investigated.

## RESULTS AND DISCUSSION

The evaluation of the physical and chemical structure of PEGTDMSO compound was carried out according to the following characterization techniques: -

### Infrared technique (FTIR)

Fig (1) illustrates the FTIR spectrum for the prepared PEGTDMSO. The characteristic bands at 945.6 and 1101.5  $\text{cm}^{-1}$  represent the stretching vibration of  $\text{CH}_2\text{-O-Si}$ , the band at 2875.6  $\text{cm}^{-1}$  for stretching vibration of  $\text{Si-O}$  and  $-\text{CH}_2$ , the bands at 2957  $\text{cm}^{-1}$  for  $\text{CH}$  aromatic, the bands at 1245.4  $\text{cm}^{-1}$  for stretching vibration of  $\text{Si-C}$  and the band at 3400  $\text{cm}^{-1}$  for stretching vibration of  $-\text{OH}$ .

### Nuclear magnetic resonance ( $^1\text{H}$ NMR)

Fig (2) illustrates the  $^1\text{H}$ NMR spectrum for PEGTDMSO. The integration 21.98, for the siloxane groups and 67.23, for ethylene glycol groups.

### Gel permeation chromatograph (GPC)

Fig. (3) illustrates the typical GPC spectrum of PEGTDMSO. The average molecular weight  $M_n$  for PEGTDMSO was 247, which was highly sensitive to the presence of small number of fraction of low molecular weight. The average molecular weight  $M_w$  of PEGTDMSO compound was 249, which was highly sensitive to the presence of small amounts by weight of high molecular (weight macro-molecules). The  $Z$  and  $Z+1$  were average molecular weights or molar mass. From different molecular weights average. These observed that the  $M_n < M_w < M_z < M_z+1$  have  $247 < 249 < 250 < 251$ . The polydispersity index was 1.004 for PEGTDMSO compound as the ratios of weight average molecular weight  $M_w / M_n$ . This ratio was unity for a polymer of uniform molecular weight and become larger as distribution become broader.

### Chemical composition of the paintings formula $Y_0 - Y_6$ .

The synthetic PEGTDMSO compound was blended with inorganic materials zinc oxide,  $\text{TiO}_2$  and silica gel as in Table (1). Toluene diiso-cyanate (TDI) was used as a curing agent at 5, 10 and 15 parts for each formula. The PEGTDMSO was used as a binder and it has also dispersant phenomena. The formulae  $Y_0 - Y_6$  were brushed on the




Fig 1 FTIR spectrum diagram for PEGTDMS compound




Fig 2 1H NMR spectrum diagram for PEGTDMS compound




Fig 3 GPC spectrum diagram for PEGTDMs compound



prepared surface of carbon steel alloy specimens. The visual inspection, physical, mechanical and chemical properties for each formed film from formula  $Y_0 - Y_6$  were investigated.

**Table (1):** Chemical formulae of PEGTDMISO cured by different ratios of curing agents TDI.

Formula Composition/ parts	$y_0$	$y_1$	$y_2$	$y_3$	$y_4$	$y_5$	$y_6$
	PEGTDMISO	45	45	45	45	45	45
ZnO	0	35	35	35	35	35	35
TiO <sub>2</sub>	0	5	5	5	5	5	5
Silica gel	0	0	1	2	3	4	5
Solvent	5	5	5	5	5	5	5
Curing agent%	5	5	5	5	5	5	5
	10	10	10	10	10	10	10
	15	15	15	15	15	15	15

#### Optimization conditions for curing agent

Table (2) illustrates the optimum conditions for the curing agent ratio of TDI. The touch dry time was the main factor, which determines the TDI concentration for curing the formed films on the surface of carbon steel alloy specimens. The inorganic additives affect each formula of  $Y_0 - Y_6$ . From the optimization studies of the curing agent TDI ratios. These indicated that the time of touch curing for formula  $Y_0 - Y_6$  were decreased by increasing inorganic additives.

**Table (2):** Data of the optimum condition for the curing agent TDI respect to time for PEG TDMISO formula at ambient condition.

The ratio of curing agent (TDI)	Touch dry time for each formed films from the formula (hr)						
	$y_0$	$y_1$	$y_2$	$y_3$	$y_4$	$y_5$	$y_6$
5%	16-22	10-12	9-10	9-10	8-9	8-9	6-8
10%	6-10	5-8	5-8	3-7	3-7	3-6	3-6
15%	3-5	2-4	2-4	2-3	1-3	1-3	1-3

### Physical properties

#### Visual inspection

The formed films from formulae  $Y_0$ -  $Y_6$  for PEGTDMSO compound were visually inspected and listed in Table (3). These data were showed that, the sealing was observed at  $Y_0$  only. On the other hand the formed films by formula  $Y_1$ - $Y_6$  were not sealing, sagging, fish eyes, shrinkable, coagulation, smoothes and homogeneity for formed coatings.

**Table (3):** Data of the visual inspection after application of the painting films formed by formula  $Y_0$  -  $Y_6$  of PEGTDMSO compound.

Formula	sealing	sagging	fish eyes	shrinking	coagulation	smoothes	homogeneity
$y_0$	Sealed						
$y_1$	no sealed						
$y_2$	no sealed						
$y_3$	no sealed	not sagging	not fish eyes appeared	no shrinking	no coagulation	high smooth	homogeneity of the formed films
$y_4$	no sealed						
$y_5$	no sealed						
$y_6$	no sealed						

#### Calculation and measuring the WFT and DFT

The results of normalization weight of wet and dry films respect to surface area were calculated and given in Table (4). These data indice that the DFT were increased with increasing the inorganic additives. Also, the measuring data of WFT and DFT were given in Table (5). These data indicate that, the DFT were increased by increasing the inorganic additives, but the WFT were decreased.

#### Adhesive forcing

The data of adhesive forces for the formed films by formula  $Y_0$  -  $Y_6$  with the surface of carbon steel alloy specimens were given in Table (5). From these data, the adhesive forces of the formed dry films by formula  $Y_0$  was failed. On the other hand, the adhesive forces of the formed films from formula  $Y_1$ - $Y_6$  were passed. These data show that, the adhesion forces increased by increasing the inorganic additives.

Table: 4 The physical measurements for each formed film from PEGTDMSO wet and dry films at ambient condition and using curing agent TDI 10%.

Sym.	Wt. of Cleaning Specimens (g)	Specimens area of one surface (Cm <sup>2</sup> )	Wt. of wet coating (g)	Normalized Wt. of wet coating per unit area (g/cm <sup>2</sup> )	Wt. of dry Coating (g)	Normalized Wt. of the formed dry coating per unit area (g/cm <sup>2</sup> )	Curing Temp. (°C)	Relative humidity	Touch dry time (hr)	Complete dry time (days)
y <sub>0</sub>	71.2375	111.8631	4.5621	0.0407	2.2825	0.0204	ambient temp.	>50	6-10	3-5
y <sub>1</sub>	71.5037	112.0357	5.1125	0.0456	3.3885	0.0302			5-8	
y <sub>2</sub>	72.0183	112.7895	5.1245	0.0301	3.4015	0.0301			5-8	
y <sub>3</sub>	70.9951	111.0053	5.1337	0.0462	3.4107	0.0307			3-7	
y <sub>4</sub>	71.3891	111.9837	5.2015	0.0464	3.4791	0.0310			3-7	
y <sub>5</sub>	71.5961	112.0007	5.2321	0.0467	3.5103	0.0313			3-6	
y <sub>6</sub>	71.9315	112.0933	5.2817	0.0471	4.5601	0.0406			3-6	

Table: 5 The physical and mechanical properties of the dry films formed from PEGTDMSO.

Symp.	WFT	DFT	Bending	Pinhole	Adhesion	Hardness	Impact	Electrical conductivity
y <sub>0</sub>	145	50	fail	fail	fail	HB	fail	Insulating at 200 Ω
y <sub>1</sub>	110	67	pass	pass	pass	F	fail	
y <sub>2</sub>	103	69	pass	pass	pass	F	pass	
y <sub>3</sub>	95	70	pass	pass	pass	H	pass	
y <sub>4</sub>	95	72	pass	pass	pass	H	pass	
y <sub>5</sub>	93	75	pass	pass	pass	2H	pass	
y <sub>6</sub>	93	78	pass	pass	pass	2H	pass	







### **Volatility of organic compounds VOC**


The Volatility of organic compounds from the paints after curing was either estimated from the formulations and / or the use of organic solvent. In this situation the volatile organic compound were defined as blended organic solvent (toluene and xylene) and PEGTDMSO. Also, some methyl groups of the PEGTDMSO compound were hydrolyzed and evaporated (emission) during the curing process and the thermal effect on the formed films. Thus, the weight of the formed films decrease until the weight was established.

### **Mechanical Properties**

The mechanical properties were investigated through hardness, bending and impact technique. The evaluation data of the mechanical properties for the formed dry films from formula Y<sub>0</sub> to Y<sub>6</sub> were given in Table (5). The mechanical properties data for the formed dry films on the surface of carbon steel alloy specimens were improved with increasing the amount of fillers (inorganic additives).

### **Mechanism**

The presence of silicon on the surface of cured films were improved the properties of the formed dry films. Mar resistance, anti-blocking and other features were enhanced by the presence of silicon. Although PEGTDMSO gives very good properties to the surface of a cured coating. This was sufficiently compatible with formulation to provide adequate storage stability. The structure of PEGTDMSO compound was terminated by hydroxyl groups in the form of Si-OH / C-OH. Which was cured by cyano groups in TDI. The polyurethane siloxane films were formed as follow:-



Where  $x$  is the degree of polymerization.

The PEGTDMSO urethane films include the variation of very important groups, such as ester, siloxane and urethane groups. These groups play an important role in improvement of the physical, mechanical and chemical properties of the dry films on the surface of carbon steel alloys.

Too, the traces of cyano groups of TDI react with hydroxyl groups of silica gel in the formation of humidity and minor hydroxyl groups on the surface of specimens. Thus, the formatted films of the polyurethane on surface of carbon steel alloy were highly compacted, adhesive, internal cohesion, hardness and also free from any pinholes. The silicon atom has tetra, penta- and hexavalent, these give good physico-chemical properties.

### Chemical properties

#### The effect of organic solvents

The effect of a mixture of benzene, toluene, xylene (ASTM D-44) on the texture morphology of the formed dry films of formulae  $Y_0 - Y_6$  were given in Table (7). These data were indicated that, organic solvents do not affect the texture of the formed dry films from formulae  $Y_1 - Y_6$ . These were indicated on the compatibility of the binder with the inorganic filler / pigments and complete reaction with curing agent TDI.

Thus, the formation of dry PEGTDMSO urethane films were resistant to the organic solvent, and can be applied in organic solvent and petroleum media.

The formed dry PEGTDMSO urethane films from formulae  $Y_1 - Y_6$  did not affected on rubbing by MEK from 15-20 times (ASTM D-4752). These results indicate that, the stability of zinc oxide and good compatible with the formed dry films.

**Table (7):** Visual inspection of the effect of the organic solvents (Toluene, Benzene, Xylene) on the formed dry films from PEGTDMSO and curing agent TDI.

Perior of immersion time (days)	Effect of the texture of the formed dry films						
	$y_0$	$y_1$	$y_2$	$y_3$	$y_4$	$y_5$	$y_6$
6	no change	no change	no change	no change	no change	no change	no change
12	no change	no change	no change	no change	no change	no change	no change
24	no change	no change	no change	no change	no change	no change	no change
48	no change	no change	no change	no change	no change	no change	no change
72	Partially swelling	Partially swelling	no change	no change	no change	no change	no change

### Evaluation of the performance of the protected films

#### Effect of 10 % $H_2SO_4$ .

The data of the effect of 10% sulfuric acid (ASTM D 468 and 610) on the formed films of formulae  $Y_0 - Y_6$  are given in Table (8). From these data, it is observed that the formed dry films of formula  $Y_0$  are affected by 10 %  $H_2SO_4$  after 10 days. On the other hand, the formatted dry films of formula  $Y_1- Y_2$  and  $Y_3-Y_4$  were chalking only up to 16 and 20 days respectively, while the formed films from  $Y_5$  &  $Y_6$  were not affected. The 1-3 corrosion spots were appeared on the surface



of the formed films of formulae  $Y_1$ -  $Y_2$  at 20 days. These ratios of corrosion spots were very low and should be neglected, (rust grade 8B ASTM D- 610), so that the formed dry films of formulae  $Y_3$ -  $Y_6$  were valid to protect the surface of carbon steel alloy against aggressive acidic media.

**Table (8):** Data of corrosion tests for the dry films formed from PEGTDMSO. and curing agent TDI on the surface of carbon steel alloy Specimens in 10%  $H_2SO_4$  for 50 days.

Period of immersion time (days)	Visual inspection for the dry films formed in 10% $H_2SO_4$						
	$Y_0$	$Y_1$	$Y_2$	$Y_3$	$Y_4$	$Y_5$	$Y_6$
1	no spots	no spots	no spots	no spots	no spots	no spots	no spots
2	no spots	no spots	no spots	no spots	no spots	no spots	no spots
3	no spots	no spots	no spots	no spots	no spots	no spots	no spots
4	no spots	no spots	no spots	no spots	no spots	no spots	no spots
8	no spots	no spots	no spots	no spots	no spots	no spots	no spots
12	chalk surface	no spots	no spots	no spots	no spots	no spots	no spots
16	chalk surface	chalk surface	chalk surface	no spots chalk	no spots chalk	no spots	no spots
20	5 spots	3spots	2spots	surface	surface	no spots	no spots

#### Effect of synthetic sea water (3.5% nacl) on the formed PEGTDMSO urethane films.

The data of the effect of synthetic sea water (3.5% NaCl) on the formed dry PEGTDMSO urethane films for 1440 hr (60 days) were given in Table (9). These results indicate that the films formed by formulae  $Y_2$  -  $Y_6$  were valid for protecting the surface of carbon steel alloy against aggressive media. Generally, due to the ratio of spots to the total surface area was less than 0.1 %, (rust grade 8B ASTM D- 610), these spots should be neglected.



**Table (9):** Corrosion tests data of the formed dry films on the surface of carbon steel alloy specimens in sea water for 60 days.

Period time (days)	Visual inspection for the formed dry films						
	Y <sub>0</sub>	Y <sub>1</sub>	Y <sub>2</sub>	Y <sub>3</sub>	Y <sub>4</sub>	Y <sub>5</sub>	Y <sub>6</sub>
3	no spots	no spots	no spots	no spots	no spots	no spots	no spots
6	no spots	no spots	no spots	no spots	no spots	no spots	no spots
9	no spots	no spots	no spots	no spots	no spots	no spots	no spots
12	1-5 spots	no spots	no spots	no spots	no spots	no spots	no spots
15	5-10 spots	no spots	no spots	no spots	no spots	no spots	no spots
18	10-14 spots	no spots	no spots	no spots	no spots	no spots	no spots
21	middle spots	no spots	no spots	no spots	no spots	no spots	no spots
24	middle spots	1-4 spots	no spots	no spots	no spots	no spots	no spots
36	much spots	low spots	no spots	no spots	no spots	no spots	no spots
48	covered spots	low spots	no spots	no spots	no spots	no spots	no spots
60	covered spots	much spots	1-5 spots	1-3 spots	1-3spots	1-3 spots	1-2 spots

### CONCLUSION

- The prepared PEGTDMSO purified and confirmed by <sup>1</sup>HNMR, FTIR and GPC.
- PEGTDMSO blended with inorganic additive ZnO<sub>2</sub>, TiO<sub>2</sub>, and silica to form formula Y<sub>1</sub> – Y<sub>6</sub>.
- The preparation surface of carbon steel alloy specimens painted by formulae Y<sub>0</sub> – Y<sub>6</sub>.
- The physical, mechanical and chemical properties of the formed films by formulae Y<sub>0</sub>- Y<sub>6</sub> recorded and discussed.
- The net results indicate the validity of the formed dry films for protection of carbon steel alloy.

**REFERENCES**

Abd El Rahman, A.M.M.; H.M. Abu Alainin and O.M. Abo-Elenien, (2004) *Egypti. Appl. Sci.*; 19(8) p.196-211.

Abo-Elenien, O.M.; O.E. Elazabawy; R.M. Aboshahba and M.A. Elsockary; (2004) *Egypti. Appl. Sci.*; 19(8) p 177-195.

Abo-Elenien, O.M. and H.M., Abu-Elainin, (2000). The effect of acidic media on the formation of siliconized films on carbon steel alloys. *Egypt. J. Petrol.*, 9, pp.13-18

Abo-Elenien, O.M. and Abu-Elainin, H.M. (2000) *Egypt. J. Petrol.*, 9 , pp.13-18.

Alagar, M.; Bilal, M., I. And Mohan, V., (1999) *British Corrosion J.*, 34 (1), pp.75-78.

Claudia, S. ; Barbel, R. ; Andrew, J. H. ; Hall, F. L. ; Klaus, U. and Sellergren, B., (2002) *Macromolecules*, 35, pp. 79-91.

Cackovich, A. and Perry, D., (2000) *Surface Coating International*, 10, pp.495 -501.

Delamo, B. ; R. Romagnoli, and V.F. Vetere, (1998). Study of the anticorrosive properties of Zn phosphate in vinyl paints. *Prog. Org. Coat.* 33(1), pp.28-35

Fream, A. J. and Magent, S. E., (2000) *Surf. Coat. Intern.*, 9, pp. 447-454.

Kim, H. J. ; Jang, J. ; Lee, Y. D. and Zin, C. W., (2002) *Macromolecules*, 35, pp.311-313.

Macqueen, D. B. and Blum, Y. D., (2001) *Surface Coating Intern.*, 84 (B1), pp.27-33.

Mayer ; H. , (1998) *Surf. Coat. Intern.*, 2 pp. 89 -93.

Sayaln ,B. J., ,(1981). Organic Compound As Corrosion Inhibitors In Different Environments. Prog. Org. Coatings , 9 (2) , PP.165-236

Sidky,P.S.and M.G. Hocking, (1999). Review of inorganic coating and coating processes for reducing wear and corrosion. , Br.Corr.J.,34(3)pp.171-183.

Sue, J.A. and Troue, H.H. (1987) Surf. Coat.Technol., 33, 169.

Tiwari,S. ; Saxena, M., (1999) Birtish Corrosion Journal 34 (3),pp. 184-191.

Townsend, H. E., (1998) Corrosion, 54(7), pp. 561 – 565.

Uyar,ik, N. ; Yalcinkaya, H. and Kizilcan, N., (2001) Surf. Coat. Inte. Part B: Coatings Transactions, 84 (B4), pp.243-336.

Zeh, H., (2000) Surface Coating International , 3, pp. 111- 118.

الأداء المفضل لمركب عديد ( الايثيلين جليكول تيرفيثالات داى ميثيل سيلوكزان) المحضر  
كمادة حامية لسبائك الحديد الكربوني لأنابيب البترول

أسامه محمود أبو الغين و حامد محمود أبو العينين\*

قسم الاستخدامات البترولية، معهد بحوث البترول، حي الزهور مدينة نصر، القاهرة، مصر.  
\*كلية الهندسة، قسم الإنتاج والتصميم، جامعه المنيا، مصر.

تم تحضير مركب عديد ( الايثيلين جليكول تيرفيثالات داى ميثيل سيلوكزان) واثبت تركيبه الكيميائي بواسطة الأشعة فوق الحمراء، الرنين المغناطيسي والفصل الجزيء للكروماتوجراف. وقد تم الحصول على سبائك الحديد الكربوني من أنابيب البترول الغير مستخدمه. وتم تحضير أسطح العينات بواسطة أوراق الصنفرة المتعددة درجات الخشونة. وقد تم تكوين عدد سبع خلطات من مركب عديد ( الايثيلين جليكول تيرفيثالات داى ميثيل سيلوكزان) مع أكسيد التيتانيوم، أكسيد الزنك ونسب مختلفة من السيليكا جيل. وأستخدم مركب الطولوين ثنائي الأيزوسيانات كعامل طبخ. وقد تم فحص الأفلام المتكونة عينيا وكذلك تم قياس الخواص الفزيائية والميكانيكية والكيميائية للأفلام المتكونة على اسطح السبائك الحديدية. وكذلك تم حساب سمك الأفلام المبللة والجافه ، التوصيل الكهربائي، انقوة الألتصاقية،الثنى الثباتيه الحرارية والصلاديه للأفلام المتكونة. وقد تم اختبار التأثير الحمضى والماء المالح المحضر على الأفلام المتكونه لمعرفة مدى مقاومتها للتآكل.